


Optical Coating Specification

DLC on Germanium 8.0 – 11.5μm

Transmission/Reflection Performance charts
G5 specification # 58 402



Specifications

Coating Specifications

Source Date	3/22/2022
Specification / Coating P/N	G5 Infrared Specification # 58 402
Coating Description	DLC on Germanium 8.0 – 11.5μm
AOI	0-20 degree
Witness Configuration	For 1mm thick Ge witness piece coated with G5 # 58 201 on side 2
Transmission Requirement	8.0 - 12.0μm > 89% Average 8.0 - 11.5μm > 91% Average
Thorium Status	Thorium Free

Environmental Qualification

Adhesion	Per MIL-C-48497A para 4.5.3.1
Abrasion	Per Mil-C-48497A para 4.5.5.1
Humidity	Per Mil-C-48497A para 4.5.3.2 24 hours
Solubility	Per Mil-C-48497A para 4.5.5.2
Salt spray	Per MIL-C-675C Para 4.5.9 for a period of 24 hours
Temperature cycle	Per MIL-C-48497A para 4.5.4.1
Windscreen	Coating shall survive 5000 revolutions of a wiper blade in a sand slurry under 40g load.

Notes

Notes	Thorium Free
-------	--------------

