



Optical Coating Specification

HEAR on Germanium 8.0 – 12.0μm

Transmission/Reflection Performance charts
G5 specification # 58 201



Specifications

Coating Specifications

Source Date	3/22/2022
Specification / Coating P/N	G5 Infrared Specification # 58 201
Coating Description	HEAR on Germanium 8.0 – 12.0μm
AOI	0-20 degree
Witness Configuration	For 1mm thick Ge witness piece coated both sides with G5 # 58 201
Transmission Requirement	8.0 - 12.0μm > 98.2% Average 8.0 - 11.5μm > 98.5% Average
Reflection Requirement	8.0 - 12.0μm < 0.3% Average, 1.0% Maximum
Thorium Status	Thorium Free

Environmental Qualification

Adhesion	Per MIL-C-48497A para 4.5.3.1
Abrasion	Per MIL-C-48497A para 4.5.3.3
Humidity	Per MIL-C-48497A para 4.5.3.2 24 hours
Solubility	Per MIL-C-48497A para 4.5.4.2
Water solubility	Per MIL-C-48497A para 4.5.5.3
Temperature cycle	Per MIL-C-48497A para 4.5.4.1

Notes

Notes	Thorium Free
-------	--------------

